

IR-26 ACCELERATOR PRODUCT DATA SHEET



PRODUCT & APPLICATION TOOLS



PRODUCT CODE	UNIT SIZE	MIXING RATIO
162105-SC	0.11 gal (0.42 L)	1 Unit per 4 gal (15 L) IR-26

DESCRIPTION

Impermitek's IR-26 Accelerator is an additive that speeds up curing time to shorten pot-life when applying some resins in low temperature ambients.

ACCESSORY COMPONENTS

The IR-26 Accelerator may be used with the following Impermitek resins:

- IR-26 Polymer Resin (Standard Grade)
- IR-26 High Temperature Grade
- IR-26 FiberLock Detailer

FEATURES

- Low VOC formulation
- Easily mixes with Impermitek's resins

STORAGE

Always store closed containers in a cool, ventilated and dry location away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures at or below 32°F (0°C) or above 77°F (25°C). Approximate maximum shelf life is 12 months when properly stored, sealed, and unmixed.

WARNINGS

When using IR-26 Standard Grade, the accelerator is recommended when the ambient temperature is from 41° to 49°F (5° - 9°C) and **required** when the temperature is from 34° to 40°F (1° - 4°C).

When using IR-26 High Temperature Grade, the Accelerator is **required** when the ambient temperature is from 41° to 68°F (5° - 20°C).

The IR-26 Accelerator should only be used with the above the specified Impermitek resins, and as recommended.

MIXING

Add the entire contents of the IR-26 Low Temp Accelerator into a 4 gallon can of IR-26 resin, then thoroughly mix the entire drum using a slow-speed (200 to 400 rpm) mechanical mixer with spiral agitator for 3 minutes, or as required, to fully incorporate the additive while avoiding aeration of the resin.

Refer to specific product data sheets for additional instructions and information regarding mixing, catalyzation, and application of individual products.

SAFETY & HANDLING

Please refer to the relevant Safety Data Sheet (SDS) prior to handling or use. Use materials in strict accordance with published guidelines. Dispose of waste materials in accordance with local, state and federal regulations.

TECHNICAL ASSISTANCE

For further information, please contact Impermitek Technical Services at +1 (780) 906-4600 or technical@impermitek.com. More information can also be found at www.impermitek.com.

Please, refer to the Impermitek installation recommendations, application manuals, and guide specifications, for complete information regarding the suitability, application, use, and handling of Impermitek products.